

Review Article

State of The Art Evolution of Adsorption Wastewater From Crude Palm Oil Industries

Meutia Mirnandaulia^{1*}, Li Idi'il Fitri¹, Mustakim^{1,2}, Muhammad Fadli Khairul³

¹ Department of Palm Oil Agribusiness, Politeknik Teknologi Kimia Industri Medan, Jalan Medan Tenggara VII, Medan Denai, Medan, Sumatera, Indonesia 20228

² Faculty of Mechanical and Automotive Engineering Technology, Universiti Malaysia Pahang Al-Sutan Abdullah, Pekan, Pahang, Malaysia 26600

³ North Sumatra Province Department of Industry, Trade, Energy, and Mineral Resources Medan Goods Quality Testing and Certification Unit Testing and Certification Section, Jalan Putri Hijau No. 6, Kesawan, Medan, Sumatera, Indonesia 20111

* Corresponding Author, email: meutiamir23@ptki.ac.id

Copyright © 2026 by Authors,
Published by Environmental Engineering Department,
Faculty of Engineering, Universitas Diponegoro
This open access article is distributed under a
Creative Commons Attribution 4.0 International License



Abstract

Wastewater from crude palm oil production is among the most concentrated agro-industrial effluents, marked by very high organic loads, suspended solids, and variable composition. Conventional treatments often struggle to consistently remove recalcitrant pollutants such as phenolics, color compounds, and emulsified oil. As a result, adsorption has gained global attention as a versatile and efficient alternative. This review summarizes recent advances in adsorption technologies for crude palm oil wastewater treatment. It highlights progress in adsorbent development, including biochar, mineral composites, layered double hydroxides, magnetic hybrids, and other engineered materials. Key removal mechanisms for organics, nutrients, and colloids are examined alongside insights from kinetic, isotherm, and thermodynamic studies. The integration of adsorption with biological, membrane, and oxidation processes is also discussed, demonstrating improved removal efficiency and effluent stability. Major challenges remain, particularly in mechanical stability, regeneration, competitive adsorption, and large-scale validation. Future research should prioritize process intensification, sustainable regeneration methods, circular-economy-based adsorbent production, and life-cycle assessment. Overall, adsorption represents a promising pathway toward more sustainable and reliable crude palm oil wastewater management

Keywords: Adsorption; CPO, environmental remediation, POME, wastewater treatment

1. Introduction

The crude palm oil (CPO) industry is one of the largest agro industrial sectors worldwide and produces more than 78.9 million metric tons of palm oil every year. The industry supports major economic growth across Southeast Asia, Africa and South America but it also generates substantial volumes of wastewater that is widely known as palm oil mill effluent or POME. Untreated or inadequately treated POME contains extremely high concentrations of chemical oxygen demand, biological oxygen demand, total suspended solids, oil and grease, phenolic compounds, organic acids and nutrients (Anwar et al., 2024; Bala et al., 2015). The discharge of this highly polluted effluent creates serious environmental

concerns that include oxygen depletion in aquatic systems, eutrophication, soil degradation and the release of greenhouse gases (Adegbola et al., 2020; Jumadi et al., 2020). The increasing strictness of environmental regulations combined with the global emphasis on sustainable industrial operations has created a critical need for efficient and economically viable wastewater treatment solutions.

A wide variety of POME treatment technologies have been investigated such as ponding systems (Jumadi et al., 2020), coagulation and flocculation (Bhatia et al., 2007), anaerobic digestion (Khadaroo et al., 2019), membrane filtration and advanced oxidation processes (Khan et al., 2025; Yashni et al., 2021). Although these technologies have been implemented in many regions, they face persistent challenges. These challenges include long hydraulic retention time, high operational cost, production of secondary sludge, sensitivity to the fluctuations of influent quality, membrane fouling and incomplete degradation of recalcitrant organic pollutants. Over the past decade, adsorption has gained significant attention as a promising alternative because it provides high efficiency with relatively low energy requirements, simple operation steps, adjustable surface chemistry and strong capability to remove a broad spectrum of contaminants (Mohammed et al., 2014; Shavandi et al., 2012). The rapid development of engineered adsorbents such as modified biochar (Wibowo et al., 2022, 2025c), clay based adsorbents (Taher et al., 2023a), layered double hydroxides (Taher et al., 2024; Wibowo et al., 2025), carbonaceous nanomaterials (Ahlawat et al., 2020) and magnetic composites (Wibowo et al., 2025) has further improved pollutant uptake, process stability and reusability.

Even though many studies have explored adsorption for POME treatment, the available scientific literature remains fragmented. Existing reviews usually concentrate on general POME treatment technologies or on biosorption using agricultural wastes or on biochar based approaches. These reviews rarely provide an integrated analysis of the evolution of adsorption technologies. They also do not systematically compare advanced engineered adsorbents and do not combine discussion on adsorption mechanisms, surface functionalization strategies, hybrid system integration and techno environmental considerations. At present there is no comprehensive review that synthesizes the full state of the art development of adsorption for wastewater from the CPO industry or that critically evaluates adsorbent performance in relation to mechanisms, modification routes, regeneration capability and scalability.

The present review aims to address these gaps. The objectives of this article are the following. First, to consolidate the progression of adsorption technologies that have been applied for CPO wastewater. Second, to provide a critical analysis of the performance of natural adsorbents, modified adsorbents and nanostructured adsorbents. Third, to discuss mechanistic insights that govern the adsorption behavior of key POME pollutants. Fourth, to highlight functionalization strategies that enhance selectivity, adsorption capacity and long term reusability. This article also integrates recent developments in hybrid systems, identifies barriers that hinder large scale application and proposes future research pathways that include sustainability assessment, circular materials design and the potential use of digital modeling. The novelty of this work is the presentation of the first comprehensive and unified assessment of adsorption technologies for wastewater from the crude palm oil industry. The review spans material advancement, mechanistic understanding, hybrid process development and future technological directions. This article provides a scientific foundation for the design of next generation adsorbents and supports the advancement of sustainable wastewater management in the global palm oil sector.

2. Methods

2.1 Review Design and Scope Definition

This study was conducted as a structured and systematic literature review aimed at synthesizing the evolution of adsorption technologies for wastewater generated from crude palm oil industries, commonly known as POME. The review was designed to critically evaluate advancements in adsorbent materials, mechanistic understanding, surface modification strategies, regeneration performance, and integration of adsorption into hybrid treatment systems. Rather than focusing solely on reporting adsorption capacity values, this review emphasizes technological progression, comparative material

performance, and practical applicability under realistic wastewater conditions. The scope includes natural adsorbents, engineered composites, nanostructured materials, and system-level integration strategies to provide a comprehensive and unified assessment of adsorption development for CPO wastewater treatment.

2.2 Literature Search Strategy

A comprehensive literature search was performed using major scientific databases, including Scopus, Web of Science, ScienceDirect, SpringerLink, Wiley Online Library, and supplementary sources accessed through Google Scholar. The search covered publications from 2000 to 2025, with particular emphasis on research published after 2015 to capture recent advances in engineered adsorbents and hybrid treatment configurations. Keyword combinations were developed to ensure coverage of both material innovation and system integration aspects. These included combinations of “palm oil mill effluent,” “POME,” “crude palm oil wastewater,” and “adsorption,” together with specific terms such as “biochar,” “layered double hydroxide,” “magnetic adsorbent,” “adsorption kinetics,” “isotherm modeling,” and “hybrid treatment.” Boolean operators were applied to refine search results and ensure relevance to adsorption-based wastewater treatment technologies.

2.3 Inclusion and Exclusion Criteria

To maintain scientific rigor and consistency, only peer-reviewed journal articles written in English were considered. Studies were included if they focused directly on adsorption applied to POME or crude palm oil wastewater and reported relevant performance indicators such as removal efficiency, adsorption capacity, kinetic modeling, isotherm analysis, regeneration performance, or integration with other treatment processes. Articles discussing adsorbent modification strategies, mechanistic interpretation, or techno-environmental evaluation were also included. Conference abstracts without accessible full text, duplicate publications, and studies unrelated to CPO wastewater were excluded. Research lacking quantitative performance data or mechanistic interpretation was also omitted to ensure analytical depth and comparability.

2.4 Data Extraction and Classification

Selected publications were systematically examined and categorized according to adsorbent type, modification approach, target pollutants, adsorption mechanisms, kinetic models, isotherm models, regeneration capability, and integration strategy. Adsorbents were grouped into biomass-based materials, biochar and activated carbon, clay minerals, layered double hydroxides, polymeric adsorbents, carbon nanomaterials, magnetic composites, and multifunctional hybrids. Quantitative parameters such as adsorption capacity, removal efficiency, optimal operating conditions, and regeneration cycles were extracted when available. Mechanistic descriptions reported by authors were synthesized and compared to identify trends in surface interaction behavior and functional group contribution.

2.5 Comparative and Mechanistic Analysis

A comparative analytical framework was developed to evaluate the progression of adsorption technologies over time. Performance comparisons considered surface area development, pore structure engineering, surface functionalization strategies, pollutant selectivity, mechanical stability, and regeneration efficiency. Mechanistic interpretation was conducted by integrating reported experimental data with established adsorption theories, including physisorption, chemisorption, ion exchange, surface complexation, and diffusion-controlled processes. Kinetic behavior was assessed through the application of pseudo-first-order, pseudo-second-order, intraparticle diffusion, and Elovich models, while equilibrium behavior was evaluated based on Langmuir, Freundlich, and Temkin isotherms. This structured analysis enabled identification of dominant interaction pathways and technological evolution patterns.

2.6 Evaluation of Hybrid Systems

Studies involving integration of adsorption with biological treatment, membrane filtration, coagulation–flotation, and advanced oxidation processes were analyzed separately to assess system-level performance enhancement. Evaluation focused on pollutant removal improvement, fouling mitigation, process stability, operational feasibility, and energy implications. Where available, techno-economic considerations and environmental sustainability aspects were qualitatively assessed. This approach allowed identification of adsorption’s role as either a pretreatment, polishing, or stabilizing unit within multi-stage treatment systems, highlighting its contribution beyond standalone application.

2.7 Limitations of the Review

This review is limited to publicly available peer-reviewed literature and does not include proprietary industrial data or unpublished pilot-scale reports. Variability in experimental conditions, including differences in adsorbent dosage, contact time, wastewater composition, and synthetic versus real POME, may influence direct performance comparison among studies. Despite these limitations, a structured evaluation framework was applied to ensure consistency, critical interpretation, and balanced assessment of technological advancement.

3. Result and Discussion

3.1 Characteristics of Wastewater from Crude Palm Oil Industries

Wastewater from crude palm oil production, commonly referred to as POME, is generated during sterilization, clarification, hydrocyclone separation and other processing stages. The wastewater constitutes one of the most concentrated agro industrial effluents because it contains a combination of suspended solids, colloidal materials, degradable organics and thermally altered compounds (Awang, 2019; Kamari et al., 2021). The physicochemical complexity of POME is influenced by fruit quality, processing conditions, extraction efficiency and the presence of residual oil (Khairuddin et al., 2016). Wastewater from crude palm oil production is characterized by extremely high organic strength, elevated suspended solids, residual oil, and significant nutrient content. The typical physicochemical characteristics of POME reported in the literature are summarized in **Table 1**. As shown, POME exhibits exceptionally high COD and BOD, reflecting its heavy organic loading, together with substantial concentrations of suspended solids and oil and grease derived from incomplete oil recovery during milling operations. In addition, the presence of phenolic compounds, organic acids, ammonium nitrogen, phosphate, and potassium contributes to strong color, odor, and eutrophication potential if discharged without adequate treatment. The wide concentration ranges reported in Table X highlight the significant variability of POME composition, which is influenced by processing conditions, fruit quality, and operational practices, thereby posing major challenges for conventional wastewater treatment systems.

Table 1. Typical characteristics of palm oil mill effluent

Parameter	Typical concentration range	Unit	References
Chemical oxygen demand (COD)	50,000–100,000	mg L ⁻¹	(Kamari et al., 2021; Liew et al., 2015; Mohammad et al., 2021)
Biological oxygen demand (BOD ₅)	15,000–30,000	mg L ⁻¹	(Bala et al., 2015; Jumadi et al., 2020; Mohammad et al., 2021)
Total suspended solids (TSS)	10,000–40,000	mg L ⁻¹	(Kamari et al., 2021; Liew et al., 2015)
Oil and grease	2,000–7,000	mg L ⁻¹	(Liew et al., 2015; Mohammad et al., 2021)
Phenolic compounds	100–1,000	mg L ⁻¹	(A Aziz et al., 2020; Nur et al., 2021)

Ammonium nitrogen (NH ₄ ⁺ -N)	30–200	mg L ⁻¹	(Kamari et al., 2021; Mohammad et al., 2021)
Phosphate (PO ₄ ³⁻ -P)	50–180	mg L ⁻¹	(Khairuddin et al., 2016; Mohammad et al., 2021)
Potassium (K ⁺)	1,000–3,000	mg L ⁻¹	(Kamari et al., 2021; Khairuddin et al., 2016)
pH	3.5–5.0	–	(Liew et al., 2015; Mohammad et al., 2021)
Temperature	70–90	°C	(A Aziz et al., 2020; Liew et al., 2015)

POME typically exhibits an exceptionally high COD often exceeding 50,000 mg/L, and BOD values commonly between 15,000 and 30,000 mg/L (Awang, 2019; Kamari et al., 2021). The effluent also contains considerable total suspended solids derived from fibrous mesocarp, fine particulates, and residual sludge. Oil and grease concentrations remain substantial due to incomplete recovery during clarification processes (Khairuddin et al., 2016). Additionally, proteins, carbohydrates, organic acids, lignocellulosic residues, phenolic compounds, and volatile fatty acids contribute to its color, turbidity, and odor (A Aziz et al., 2020). The characteristics of POME vary among mills due to differences in press pressures, sterilization temperatures, extraction methods, and water usage patterns (Zainal, 2018). Seasonal variation in fruit composition and changes in oil recovery efficiency further contribute to fluctuations in pollutant concentration, complicating treatment strategies (Khadaroo et al., 2019). Apart from the organic fraction, POME contains nutrients such as ammonium nitrogen, phosphate, and potassium that can promote eutrophication if discharged untreated (Khairuddin et al., 2016).

High temperature and low pH conditions encourage anaerobic microflora growth and fermentation product formation, contributing to the strong odor and dark coloration of raw POME (A Aziz et al., 2020). The effluent's high biodegradability promotes methane and carbon dioxide production during microbial decomposition (Low et al., 2021). Current environmental regulations require effluent discharge to meet strict limits for COD, BOD, suspended solids, and oil content, yet many systems struggle due to the effluent's high pollutant strength and variability (Kamari et al., 2021; Zainal, 2018). This complexity creates a strong need for robust and flexible treatment technologies. Adsorption-based systems are increasingly studied due to their ability to handle fluctuating influent conditions and effectively remove phenolics, residual oil, and colored compounds (Chan et al., 2024; Kamari et al., 2021).

3.2 Evolution of POME Treatment Technologies

The treatment of wastewater from crude palm oil production has evolved over several decades in response to stricter environmental regulations and the growing need for sustainable industrial practices. Early processing facilities relied almost entirely on natural degradation through extensive ponding systems. Over time, a wide range of physicochemical, biological and advanced treatment technologies have been explored to improve efficiency, reduce environmental burdens and achieve compliance with regulatory discharge limits. The ponding system is the oldest and most widely adopted method in the palm oil industry (Chan et al., 2024) and reported as conventional methods in treating POME in Malaysia (Liew et al., 2015). It typically consists of a series of anaerobic, facultative and maturation ponds. These ponds rely on natural microbial degradation and long retention periods to reduce the very high organic load of POME. Although relatively simple and inexpensive to construct, ponding systems require large land areas and remain sensitive to hydraulic overload and climatic variability. The long retention time also leads to high emissions of methane and contributes to odor problems. Moreover, ponding alone is often insufficient to meet the increasingly strict discharge standards imposed in many producing countries.

Physicochemical methods were introduced to overcome the limitations of natural ponding. These methods include flotation-coagulation (Poh et al., 2014), coagulation and flocculation (Azmi et al., 2023), coagulation-sedimentation-extraction (Subhash Bhatia, 1970), air flotation (Ng et al., 1988) and combined organic precipitation, electrocoagulation, and electrooxidation (Khongkliang et al., 2024). Coagulant

agents promote the aggregation of suspended solids and colloidal oil, improving separation efficiency (Zinatizadeh et al., 2017). Although effective in reducing turbidity and suspended solids, physicochemical treatments generate large amounts of sludge that require further handling. Chemical costs can also be substantial, especially for mills with limited wastewater treatment budgets. In addition, many dissolved organic compounds remain in solution after coagulation and therefore require secondary treatment. Biological technologies such as aerobic processes, anaerobic digestion, sequential batch reactors and expanded granular sludge bed systems provide significant reductions in biological oxygen demand and chemical oxygen demand (Chan et al., 2010; Singh and Srivastava, 2011). Anaerobic digestion is particularly attractive because it produces biogas that can be used as an energy source (Appels et al., 2011; Obileke et al., 2021). However, biological systems demand careful control of pH, temperature and loading rate. They also suffer from shock load effects when the composition or volume of POME changes rapidly. Aerobic systems can achieve high degrees of organic removal but they require energy intensive aeration and produce large quantities of excess biomass.

Membrane based technologies such as microfiltration, ultrafiltration, nanofiltration and reverse osmosis have shown promising results in removing suspended solids, colloidal oil and dissolved organic compounds (Ho et al., 2025; Pandey et al., 2012). These technologies produce high quality effluent but they are hampered by membrane fouling, high maintenance costs and the need for pre treatment to prevent clogging. Concentrate streams generated by membrane systems also require additional management. Hybrid technologies that combine biological, physicochemical and membrane processes have been proposed to enhance treatment efficiency (Gusti Wibowo et al., 2024, 2024). These integrated systems aim to maximize removal of organic load while minimizing operational limitations. However, hybrid configurations often require complex operation strategies and may not be economically feasible for small or medium size mills. A clear trend in recent research is the increasing interest in adsorption based treatment. Adsorption provides several distinct advantages that address the weaknesses of earlier technologies. It functions effectively across a wide range of influent conditions, offers strong selectivity toward specific pollutants and produces minimal secondary waste. Adsorbents can be regenerated multiple times, which reduces overall cost. The development of advanced materials has greatly increased adsorption capacity and process reliability. These advantages explain why adsorption has emerged as a key focus in the evolution of POME treatment strategies and why a deeper understanding of adsorption mechanisms and material innovations is essential for further progress.

3.3 Adsorption Fundamentals in Wastewater Treatment

Adsorption is a surface based process in which dissolved or suspended contaminants are transferred from the liquid phase onto the surface of a solid material known as an adsorbent (Nageeb, 2013). This process is governed by the physicochemical interactions between the pollutant molecules and the active sites of the adsorbent (Wibowo, et al., 2025). Adsorption has gained considerable attention for the treatment of POME because the effluent contains a mixture of dissolved organics, colloidal oil droplets, pigments and phenolic compounds that can interact strongly with engineered surfaces. The versatility of adsorption allows the removal of compounds that are resistant to biological degradation and that often remain in the treated effluent produced by conventional technologies. Adsorption mechanisms relevant to POME include physical attraction forces, chemical bonding, electrostatic interaction, ion exchange and surface complexation (Ahsan and Ismail, 2019; Jatoi et al., 2023; Kacaribu et al., 2025). Physical adsorption involves weak van der Waals interactions and usually occurs when the adsorbent possesses a high surface area and a well developed pore structure (Gunawardene et al., 2022). Chemical adsorption involves the formation of stronger interactions that include covalent bonding, complex formation or specific affinity between functional groups on the adsorbent surface and the pollutant molecules (Gunawardene et al., 2022). POME contains phenolic compounds, colored pigments, organic acids and residual oil droplets that can participate in both physical and chemical adsorption depending on the nature of the adsorbent (Badawi et al., 2021; Hoe et al., 2020).

The performance of adsorption systems is commonly described using isotherm models (Naswir et al., 2021). The Langmuir model is often used to represent monolayer adsorption on a surface with uniform active sites (Song et al., 2013). The Freundlich model is suitable for heterogeneous surfaces and describes multilayer adsorption (Saadi et al., 2015). The Temkin model considers the effect of indirect adsorbate interactions on the adsorption process (Pursell et al., 2012). These models provide insight into the maximum adsorption capacity, the strength of interaction and the heterogeneity of the surface. Studies on POME often reveal that engineered adsorbents exhibit mixed adsorption behavior because the effluent contains multiple pollutant classes that interact differently with each type of active site. Kinetic models help to explain the rate of pollutant transfer from the liquid phase to the adsorbent surface. The pseudo first order and pseudo second order models are widely applied in adsorption studies involving POME (Lin and Wang, 2009; Revellame et al., 2020). The pseudo first order model assumes that the rate is influenced by the difference between the equilibrium and the actual adsorption at a given time (Naswir et al., 2021). The pseudo second order model often fits better because it reflects systems dominated by chemisorption or strong interaction with functional groups (Taher et al., 2023a). Other models such as the intraparticle diffusion model and the Elovich model provide information about the diffusion of pollutants inside the pores and the role of surface heterogeneity.

Several operational parameters influence the overall performance of adsorption for POME treatment. The pH of the solution affects the charge of both the pollutant molecules and the adsorbent surface (Adeleke et al., 2017). Lower pH conditions tend to increase interactions with phenolic compounds while higher pH conditions can enhance the removal of certain organic acids (Hashim et al., 2018; Rahmanian et al., 2014; Solomakou and Goula, 2021). Particle size determines the available surface area and influences external mass transfer (Hajilari et al., 2019; Mathews and Zayas, 1989). Adsorbent dosage affects the number of active sites and the degree of surface saturation (Mondal et al., 2008). Temperature influences the rate of diffusion and the strength of interaction (Baraka, 2015; Zehtab and Tarighat, 2018). The chemical nature of the surface, including the presence of oxygen containing groups, metal species or hydrophobic domains, greatly affects the selectivity toward various pollutants. Understanding these fundamental principles is essential for designing high performance adsorbents for POME treatment. The complexity of POME requires adsorbents with a combination of high surface area, tailored pore distribution, strong affinity toward aromatic compounds and adequate stability under acidic and high temperature conditions. These considerations have encouraged the rapid development of natural adsorbents, modified adsorbents, carbon based materials, layered minerals and nanostructured composites that will be discussed in the following section on state of the art adsorbent evolution.

3.4 State of the Art Adsorbents for CPO Wastewater

Recent advances in materials engineering have greatly expanded the range of adsorbents available for the treatment of wastewater from the crude palm oil industry. The complexity of POME requires adsorbents that possess high surface area, tailored pore structures, strong affinity toward aromatic and hydrophobic compounds and stable performance under acidic conditions. Research efforts over the last decade have focused on material classes that include lignocellulosic biomass, biochar, clays, layered double hydroxides, carbon based engineered materials, polymeric adsorbents and hybrid nanostructures. Each material type provides unique advantages in terms of cost, selectivity and reusability.

Agricultural waste based adsorbents represent one of the earliest classes investigated for POME treatment (Hamzah et al., 2025). These adsorbents include palm fiber (Alhogbi et al., 2021), palm kernel shell (Jumasiah et al., 2005), coconut shell (Budihardjo et al., 2021), rice husk (Foo and Hameed, 2009) and other lignocellulosic residues. Their availability and low cost make them attractive for industries located near plantations. These materials exhibit natural porosity and contain functional groups such as hydroxyl and carboxyl groups that interact with suspended solids and dissolved organics. However, untreated biomass usually has limited surface area and often shows low adsorption capacity for phenolic compounds

and oil droplets. As a result, chemical and thermal modification have been introduced to enhance pore development and surface chemistry (Mozetič, 2019; Rehman et al., 2019).

Biochar and activated biochar derived from palm biomass have become important adsorbents for POME. Biochar provides a highly carbon rich structure with abundant micro and mesopores (Taher et al., 2023; Wibowo et al., 2025). Thermal activation produces greater surface area while chemical activation introduces oxygen containing groups that improve affinity toward organic acids and colored compounds. Engineered biochar composites that incorporate metal oxides (Dey and Ahmaruzzaman, 2023), clay minerals or polymeric binders further enhance stability and selectivity (Liu, 2007; Scheuermann Filho et al., 2021). These advanced biochars show significant improvement in removing residual oil and persistent color forming substances. The flexibility of biochar synthesis allows fine control of pore distribution and surface functionality, which is critical for handling diverse pollutants present in POME.

Clay based materials such as bentonite, kaolin, montmorillonite and sepiolite have also been examined due to their layered structures and high cation exchange capacity (Borah et al., 2022; Perelomov et al., 2021). Clays provide strong affinity toward polar compounds and can effectively remove suspended solids and colloidal oil (Swartzen-Allen and Matijevic, 1974). Surface modification using organic surfactants or metal ions enhances their interaction with hydrophobic and aromatic molecules (Chao et al., 2013). Layered double hydroxides represent another mineral based material with tunable interlayer spacing and strong anion exchange capability (Tang et al., 2022). These materials are effective for removing organic acids, color forming molecules and nutrient based contaminants. Their regeneration through ion exchange also contributes to long term applicability.

Carbon based engineered materials such as activated carbon, carbon nanotubes and graphene related materials have been extensively studied due to their exceptionally high surface areas and strong affinity toward aromatic pollutants. Activated carbon remains one of the most effective adsorbents for POME because of its well developed microporous structure and stable performance under a wide range of pH and temperature conditions (Hayawin et al., 2023; Parthasarathy et al., 2016). Carbon nanotubes and graphene oxide introduce unique properties that include strong pi electron interactions, high adsorption rate and selective affinity toward phenolic compounds (Catherine et al., 2018; Lin and Xing, 2008). The cost of these materials is relatively high but ongoing advances in synthesis and the use of biomass precursors have improved economic feasibility.

Polymeric adsorbents such as ion exchange resins and synthetic polymers with specific functional groups provide high selectivity toward particular pollutant classes (Hubicki and Koodynsk, 2012; Samiey et al., 2014). These materials can be designed to target organic acids, dyed compounds or dissolved aromatic molecules. Their mechanical strength and resistance to chemical degradation make them suitable for repeated regeneration. However, polymeric adsorbents must be carefully matched with the composition of POME to avoid rapid fouling by oil droplets and suspended solids.

Emerging nanostructured adsorbents have introduced a new level of performance for POME treatment. These include magnetic nanocomposites, metal oxide impregnated carbon materials, polymer coated nanoparticles and hybrid structures that combine the strengths of mineral, carbon and polymer components. Magnetic composites are particularly attractive because they can be rapidly separated using magnetic fields and therefore minimize secondary waste and processing time. Nanostructured materials allow precise control of interaction sites and can achieve very high adsorption capacity due to their large surface to volume ratio. Their main challenges relate to material cost, potential toxicity and the need for safe recovery systems.

The wide diversity of adsorbents reported in the literature shows that adsorption for POME treatment has progressed from simple agricultural wastes to highly engineered multifunctional materials. Comparative studies consistently demonstrate that advanced composites and nanostructured systems offer the highest removal performance for color, phenolic compounds and residual oil. However, natural and modified biochar remain attractive for large scale applications because of low cost and renewable origin.

The evolution of adsorbent materials reflects a shift toward designs that combine high capacity, strong selectivity, rapid regeneration and operational stability in complex wastewater matrices.

3.5 Functionalization and Modification Approaches

The development of high performance adsorbents for wastewater from the crude palm oil industry has increasingly focused on functionalization and modification strategies. These strategies aim to improve surface chemistry, increase pore accessibility, enhance affinity toward specific pollutants and extend material durability during repeated adsorption cycles. The complex composition of POME, which contains a mixture of phenolics, organic acids, colored compounds, oil droplets and suspended solids, requires adsorbents with tailored surface properties and stable active sites. Functionalization offers a powerful route to meet these requirements. Chemical activation is one of the most widely used modification approaches (Panwar and Pawar, 2022). This process involves the use of activating agents such as potassium hydroxide, phosphoric acid or zinc chloride to promote pore formation and to introduce oxygen containing surface groups. These groups enhance interaction with phenolic compounds and other polar organics commonly found in POME. Chemical activation also increases the proportion of mesopores, which facilitates the diffusion of larger molecules such as residual oil and colored components (Rehman et al., 2019). The enhanced porosity and surface functionality significantly increase adsorption capacity and improve mass transfer behavior.

Surface oxidation is another approach that alters the chemical nature of the adsorbent. Treatments that involve controlled exposure to oxidizing agents create functional groups such as carboxyl, carbonyl and hydroxyl groups (Langley and Fairbrother, 2007; Pradhan and Sandle, 1999). These groups improve the affinity of the adsorbent toward organic acids and aromatic compounds through hydrogen bonding and complex formation. Oxidation also increases hydrophilicity, which reduces fouling by oil droplets and helps maintain adsorption performance under prolonged operation. Grafting strategies involve the introduction of new functional groups or polymers onto the surface of the adsorbent. These functional groups are selected to target specific contaminants present in POME. For example, amine functionalization improves binding of phenolic compounds, while sulfonated groups enhance affinity toward colored pigments and reactive organics (Xu et al., 2019; Yang et al., 2025). Grafted polymers can introduce selective binding sites that increase removal efficiency even when the wastewater contains competing molecules. This targeted design allows adsorbents to achieve high selectivity while maintaining adequate capacity. Metal and metal oxide impregnation has emerged as a highly effective method for improving adsorption toward recalcitrant compounds. Metals such as iron, aluminum or magnesium create surface active sites that facilitate complexation with phenolic molecules and other aromatic organics. Metal oxides such as iron oxide, manganese oxide or titanium oxide provide catalytic or redox active sites that enhance removal of color forming substances (Huang and Zhang, 2020; Mapossa et al., 2021; Zhu et al., 2020). Impregnation also improves structural stability and prevents pore collapse during thermal regeneration.

Composite formation is another important modification technique. Composites that combine biochar with clay minerals, polymer matrices or layered double hydroxides create multifunctional adsorbent systems with complementary properties. Clay based components contribute high cation exchange capacity, while polymeric components provide mechanical strength and resistance to acid attack. Layered double hydroxides offer strong anion exchange capability and can remove organic acids and colored anions. These composite materials address the limitations of single component adsorbents and improve overall pollutant removal across multiple contaminant categories. Magnetic functionalization has attracted considerable attention because it allows rapid separation of the adsorbent from wastewater using magnetic fields (Zeng et al., 2022). Magnetic nanoparticles embedded within carbon based or mineral based matrices do not significantly reduce surface area and provide an efficient route for adsorbent recovery. This approach reduces handling time, minimizes secondary sludge generation and improves feasibility for continuous flow systems. Magnetic composites are especially valuable for high strength wastewater such as POME where large volumes of solids must be quickly removed. Functionalization

strategies have greatly improved adsorption performance for POME treatment and have enabled the development of advanced materials with high capacity, strong selectivity and excellent regeneration capability. The combination of chemical activation, surface oxidation, grafting, metal impregnation and composite formation has produced adsorbents that outperform traditional materials by a significant margin. These advancements form a critical foundation for the next stage of innovation which involves integrating adsorption with other treatment technologies to achieve higher efficiency and greater process sustainability. This topic is discussed in the following section.

3.6 Integration of Adsorption with other Technologies

The increasing complexity of wastewater from the crude palm oil industry has encouraged the development of integrated treatment systems that combine adsorption with complementary technologies. These combinations aim to enhance pollutant removal efficiency, overcome specific limitations of single treatment methods and improve overall process stability. Integration allows selective targeting of contaminants that are resistant to biological degradation, prone to membrane fouling or difficult to remove through physicochemical methods alone. The use of hybrid systems has therefore become an important trend in advanced POME treatment research. The combination of adsorption with biological treatment is one of the most extensively studied approaches. Biological systems such as anaerobic digestion and aerobic treatment are effective for degrading biodegradable organic matter (Du and Li, 2017; Reineke, 2001), but they frequently struggle with phenolics, colored compounds and colloidal oil droplets. These resistant pollutants can inhibit microbial activity and reduce overall system stability. The addition of an adsorption step reduces the concentration of inhibitory substances and enhances microbial performance. Adsorption can also polish the biologically treated effluent by removing residual color and dissolved organics. This combination improves effluent quality while maintaining low operational cost.

Adsorption has also been integrated with membrane based processes (Schideman et al., 2007). Membrane filtration provides high quality effluent and can achieve excellent removal of suspended solids, oil droplets and dissolved organics (Keyvan Hosseini et al., 2022). However, membrane fouling remains a major challenge, especially when treating high strength wastewater such as POME. The inclusion of an adsorption stage before membrane filtration reduces the concentration of foulants, which prolongs membrane lifespan and decreases the frequency of cleaning. In some configurations, adsorbents are applied within the membrane bioreactor system to stabilize biological activity and to protect the membrane surface from rapid clogging. This approach results in more consistent performance and lower operational cost. Advanced oxidation processes have been coupled with adsorption to address recalcitrant pollutants that resist conventional degradation. Oxidation methods such as ultraviolet based processes, ozone based processes and hydrogen peroxide based processes produce reactive species that break down complex organic molecules and convert them into more adsorbable forms (Mahmoodi and Pishbin, 2025; Stefan, 2017). When combined with adsorption, oxidation serves as a pretreatment step that improves the accessibility of pollutant fragments to the adsorbent surface. Conversely, adsorption used after oxidation can remove intermediate by products that may be toxic or colored. This synergy significantly enhances the removal of phenolic compounds, pigments and persistent organic substances in POME.

Hybrid systems that incorporate adsorption with coagulation or flotation have also been developed (Gusti Wibowo et al., 2024). Coagulation improves the removal of suspended solids and colloidal oil, which reduces physical blockage on the surface of the adsorbent. In turn, adsorption eliminates dissolved organics that remain after coagulation. This sequence results in more efficient separation and clearer final effluent. Flotation, particularly air flotation, benefits from adsorption because adsorbents can assist the attachment of hydrophobic molecules to rising bubbles, thereby improving separation efficiency. Techno economic evaluations show that integrated systems provide higher treatment efficiency with lower overall cost compared to single unit processes. Energy consumption is reduced because adsorption stabilizes biological systems and reduces membrane fouling. Chemical consumption is lowered because advanced composites require less regeneration and maintain higher capacity over

multiple cycles. At the same time, environmental impacts are minimized because integrated systems produce less secondary waste and achieve more consistent removal of pollutants that contribute to odor, color and greenhouse gas formation. The success of integrated systems demonstrates that adsorption can serve as a central component within multi stage treatment strategies for POME. By combining the strengths of biological degradation, membrane filtration, chemical oxidation and physicochemical separation, adsorption enhances both treatment efficiency and operational sustainability. These hybrid systems provide a promising pathway for scaling up advanced POME treatment in commercial palm oil mills. Their future development will require careful consideration of cost, process control, materials regeneration and environmental performance, topics that will be explored in the following section on challenges and future perspectives.

3.7 Challenges, Knowledge Gaps, and Future Perspectives

Although adsorption has demonstrated strong potential for palm oil mill effluent treatment, several important challenges remain before the technology can be widely implemented at industrial scale. These challenges originate from the complex nature of POME, variability in operating conditions, inconsistencies in adsorbent regeneration and limitations in long term performance. Addressing these issues is essential to ensure reliable, cost effective and sustainable process operation. A major challenge lies in the structural instability of many low cost and bio based adsorbents during continuous treatment. Materials such as biochar, agricultural residues and clay composites tend to undergo swelling, fragmentation and loss of active sites when exposed to fluctuating pH, high temperature or strong hydraulic forces in column systems. This instability leads to pressure drop, clogging and a gradual decline in adsorption capacity. Only a limited number of studies have assessed the mechanical durability of adsorbents under realistic flow conditions. Therefore, research on strengthening methods, binder selection, mineral reinforcement and composite formation remains an urgent need.

Another concern is the regeneration efficiency of spent adsorbents. Chemical and thermal regeneration can restore a portion of the adsorption capacity, but repeated cycles often lead to pore collapse, surface oxidation and reduced performance. In many cases, regeneration consumes significant amounts of chemicals and energy, which increases operational cost and creates secondary waste. There is a need for regeneration strategies that use mild conditions, produce fewer residues and are compatible with large scale operation. Promising options include solvent free regeneration, catalytic oxidation at low temperature and in situ biological regeneration. Process variability is also a significant challenge. POME composition changes depending on fruit quality, milling operations and seasonal production. These variations influence adsorption behavior, breakthrough time and bed exhaustion. Most studies rely on synthetic or laboratory scale POME with limited variability, which does not fully represent industrial wastewater. Future research should focus on dynamic testing using real POME with different characteristics. Advanced modelling that integrates adsorption kinetics with hydraulic behavior can support the design of more stable systems.

Knowledge gaps also exist in the interaction between adsorption and other treatment units in integrated systems. Although hybrid processes have been developed, there is insufficient understanding of competitive adsorption between organic matter, surfactants, oil droplets and phenolic compounds. The presence of biological solids or oxidation intermediates may also block active sites or modify surface chemistry. More detailed molecular level investigation is needed to clarify these interactions. Techniques such as in situ spectroscopy, surface energy mapping and computational simulation can provide valuable insight. From a sustainability perspective, large scale application requires a clear evaluation of the environmental footprint of adsorbent production, operation and disposal. Life cycle assessment studies are still scarce for POME treatment. There is a need to quantify energy demand, greenhouse gas emissions and resource consumption associated with various adsorbent types. Furthermore, strategies for safe disposal or valorization of spent materials must be developed. Options include use as fuel, incorporation

into building materials, recovery of adsorbed organics or conversion into soil amendments. Each option requires further validation under real conditions.

Despite these challenges, the field offers several promising opportunities. Advanced composites such as biochar based layered double hydroxides, magnetic materials and clay reinforced hybrids have shown strong structural stability and high affinity for complex pollutants. Their tunable surface properties allow selective removal of targeted compounds, while magnetic separation ensures rapid recovery. The use of local waste materials for adsorbent production supports circular economy principles and reduces treatment cost. In addition, the integration of adsorption with biological, membrane and advanced oxidation processes provides a pathway toward highly efficient multi stage treatment systems. Future research should prioritize the development of mechanically durable adsorbents, standardized regeneration methods, full scale column testing and comprehensive techno economic analysis. Improved modelling tools, combined with machine learning, may assist in predicting breakthrough behavior under complex wastewater conditions. Ultimately, the advancement of adsorption based technologies will support cleaner production in the palm oil industry and contribute to more sustainable management of industrial wastewater.

4. Conclusions

Wastewater from crude palm oil production remains among the most challenging agro-industrial effluents due to its extremely high organic strength, complex colloidal matrix, and pronounced variability in composition. Conventional treatment technologies provide partial remediation but frequently fail to ensure consistent compliance with discharge standards, particularly for recalcitrant contaminants such as phenolic compounds, color-forming substances, and fine oil droplets. These persistent limitations have driven increasing interest in adsorption-based treatment, which offers high removal efficiency, operational flexibility, and strong compatibility with existing treatment units. The evolution of adsorption technologies for palm oil mill effluent has progressed from low-cost agricultural residues to engineered biochar, mineral hybrids, layered double hydroxides, and magnetic composites with enhanced surface area, tailored selectivity, and improved recoverability. Recent developments demonstrate that adsorption delivers its greatest value when implemented within hybrid treatment configurations that integrate biological, membrane, or oxidation-based processes. Such systems reduce inhibitory pollutant loading, stabilize downstream units, and provide a more resilient and adaptable treatment pathway for complex effluents such as POME. Despite these advances, industrial implementation remains constrained by several unresolved challenges. Structural instability under continuous-flow conditions, declining performance during repeated regeneration cycles, limited understanding of competitive adsorption in real POME, and the scarcity of large-scale validation studies continue to hinder technology transfer. In addition, the environmental and economic implications of adsorbent production, regeneration, and end-of-life management remain insufficiently quantified. The most critical next step for the field is a decisive shift from laboratory-scale material performance toward application-oriented validation under realistic operating conditions. Priority should be given to continuous-flow and pilot-scale studies using real POME, where the combined effects of wastewater variability, oil and grease fouling, hydraulic stress, and long-term regeneration can be rigorously evaluated. In parallel, adsorption units must be deliberately designed as functional components within existing treatment trains, serving as targeted polishing or protective steps that mitigate biological inhibition, membrane fouling, and effluent instability rather than as stand-alone solutions. This transition from material-centric innovation to system-level design, durability, and operational compatibility will ultimately determine the practical and environmental impact of adsorption-based technologies. Achieving this shift will enable adsorption to move beyond promising laboratory results and become a deployable, sustainable solution supporting cleaner production and improved wastewater management in major palm oil producing regions.

Declaration of Generative AI and AI-assisted Technologies in the Writing Process

During the preparation of this work the author(s) used ChatGPT in order to improve the readability and fix the grammatical errors. After using this tools/service, the author(s) reviewed and edited the content as needed and take(s) full responsibility for the content of the published article.

Ethics Statement

This study no need ethical clearance.

CRedit Authors Atatement

Meutia Mirnandaulia¹, Li Idi'il Fitri, Mustakim, Muhammad Fadli Khairul: Conceptualization, Writing Original Manuscript, Writing-Review And Editing, Finalization

References

- A Aziz, M.M., Kassim, K.A., ElSergany, M., Anuar, S., Jorat, M.E., Yaacob, H., Ahsan, A., Imteaz, M.A., and Arifuzzaman. 2020. Recent advances on palm oil mill effluent (POME) pretreatment and anaerobic reactor for sustainable biogas production. *Renewable and Sustainable Energy Reviews* 119, 109603.
- Adegbola, G.M., Adeoye, A.O., and Olatunde, S.K. 2020. A review of biodegradation as a panacea for palm oil mill effluents (POME) pollution. *International Journal of Current Microbiology and Applied Sciences* 9, 2506–2516.
- Adeleke, A.O., Latiff, A.A.Ab., Al-Gheethi, A.A., and Daud, Z. 2017. Optimization of operating parameters of novel composite adsorbent for organic pollutants removal from POME using response surface methodology. *Chemosphere* 174, 232–242.
- Ahlawat, W., Kataria, N., Dilbaghi, N., Hassan, A.A., Kumar, S., and Kim, K.-H. 2020. Carbonaceous nanomaterials as effective and efficient platforms for removal of dyes from aqueous systems. *Environmental Research* 181, 108904.
- Ahsan, A., and Ismail, A.F. 2019. Nanotechnology in water and wastewater treatment: theory and applications, *Micro & nano technologies series*. Elsevier, Amsterdam.
- Alhogbi, B.G., Altayeb, S., Bahaidarah, Effat.A., and Zawrah, M.F. 2021. Removal of anionic and cationic dyes from wastewater using activated carbon from palm tree fiber waste. *Processes* 9, 416.
- Anwar, D., Simanjuntak, E.E., Sitepu, I., Kinda, M.M., Nainggolan, E.A., and Wibowo, Y.G. 2024. Thermophilic digestion of palm oil mill effluent: enhancing biogas production and mitigating greenhouse gas emissions. *Jurnal Presipitasi* 21, 734–746.
- Appels, L., Lauwers, J., Degreè, J., Helsen, L., Lievens, B., Willems, K., Van Impe, J., and Dewil, R. 2011. Anaerobic digestion in global bio-energy production: potential and research challenges. *Renewable and Sustainable Energy Reviews* 15, 4295–4301.
- Awang, N. 2019. Physicochemical, cytotoxicity and genotoxicity assessment of palm oil mill effluent on V79 cells. *Applied Ecology and Environmental Research*. 17.
- Azmi, L.H.M., Elaissari, A., Fatehah, M.O., Aziz, H.A., and Hung, Y.-T. 2023. Evaluation of coagulation-flocculation treatment technologies in palm oil effluent management, in: Wang, L.K., Wang, M.-H.S., Hung, Y.-T. *Industrial Waste Engineering, Handbook of Environmental Engineering*. Springer International Publishing, Cham 509–551.
- Badawi, A.K., Abd Elkodous, M., and Ali, G.A.M. 2021. Recent advances in dye and metal ion removal using efficient adsorbents and novel nano-based materials: an overview. *RSC Advances* 11, 36528–36553.
- Bala, J.D., Lalung, J., and Ismail, N. 2015. Studies on the reduction of organic load from palm oil mill effluent (POME) by bacterial strains. *International Journal of Recycling of Organic Waste in Agriculture* 4, 1–10.

- Baraka, A. 2015. Investigation of temperature effect on surface-interaction and diffusion of aqueous-solution/porous-solid adsorption systems using diffusion-binding model. *Journal of Environmental Chemical Engineering* 3, 129–139.
- Bhatia, S., Othman, Z., and Ahmad, A.L. 2007. Coagulation–flocculation process for POME treatment using *Moringa oleifera* seeds extract: optimization studies. *Chemical Engineering Journal* 133, 205–212.
- Borah, D., Nath, H., and Saikia, H. 2022. Modification of bentonite clay & its applications: a review. *Reviews in Inorganic Chemistry* 42, 265–282.
- Budihardjo, M.A., Wibowo, Y.G., Ramadan, B.S., Serunting, M.A., Yohana, E., and Syafrudin. 2021. Mercury removal using modified activated carbon of peat soil and coal in simulated landfill leachate. *Environmental Technology & Innovation* 24, 102022.
- Catherine, H.N., Ou, M.-H., Manu, B., and Shih, Y. 2018. Adsorption mechanism of emerging and conventional phenolic compounds on graphene oxide nanoflakes in water. *Science of The Total Environment* 635, 629–638.
- Chan, Y.B., Aminuzzaman, M., Win, Y.F., Djearmane, S., Wong, L.S., Guha, S.K., Almohammadi, H., Akhtaruzzaman, Md., and Tey, L.H. 2024. *Garcinia mangostana* l. Leaf-extract-assisted green synthesis of CuO, ZnO and CuO-ZnO nanomaterials for the photocatalytic degradation of palm oil mill effluent (POME). *Catalysts* 14, 486.
- Chan, Y.J., Chong, M.F., and Law, C.L. 2010. Biological treatment of anaerobically digested palm oil mill effluent (POME) using a lab-scale Sequencing Batch Reactor (SBR). *Journal of Environmental Management* 91, 1738–1746.
- Chao, H.-P., Lee, C.-K., Juang, L.-C., and Han, Y.L. 2013. Sorption of organic compounds, oxyanions, and heavy metal ions on surfactant modified titanate nanotubes. *Industrial and Engineering Chemistry Research*. 52, 9843–9850.
- Dey, A.K., and Ahmaruzzaman, Md. 2023. Recent advances in nano-metal oxide-biochar composites for efficient removal of environmental contaminants. *Reviews Environmental Contamination* 261, 6.
- Du, H., and Li, F. 2017. Characteristics of dissolved organic matter formed in aerobic and anaerobic digestion of excess activated sludge. *Chemosphere* 168, 1022–1031.
- Foo, K.Y., and Hameed, B.H. 2009. Utilization of rice husk ash as novel adsorbent: A judicious recycling of the colloidal agricultural waste. *Advances in Colloid and Interface Science* 152, 39–47.
- Gunawardene, O.H.P., Gunathilake, C.A., Vikrant, K., and Amaraweera, S.M. 2022. Carbon dioxide capture through physical and chemical adsorption using porous carbon materials: a review. *Atmosphere* 13, 397.
- Gusti Wibowo, Y., Safitri, H., Khairurrijal, K., Taher, T., Ode Arham, L., Jarwinda, Jasipto, A., Akbari Danasla, M., Fadhilah, R., Kharisma Army, E., Zul Hakim, H., Tawfiequrahman Yuliansyah, A., and Tri Bayu Murti Petrus, H. 2024. Recent advances in acid mine drainage treatment through hybrid technology: comprehensive review of scientific literature. *Environmental Nanotechnology, Monitoring & Management* 21, 100945.
- Hajilari, M., Shariati, A., and Khosravi-Nikou, M. 2019. Mass transfer determination of ethanol adsorption on activated carbon: kinetic adsorption modeling. *Heat Mass Transfer* 55, 2165–2171.
- Hamzah, M.A.A.M., Yusof, N., Zaini, M.A.A., Zakaria, Z.A., Jaafar, J., and Misdan, N. 2025. Advancing heavy metal removal from industrial wastewater using oil palm waste-based adsorbent: toward efficient adsorption and commercialization. *Current Pollution Reports* 11, 52.
- Hashim, H., Wan Ahmad, W.Y., Zubairi, S.I., and Maskat, M.Y. 2018. Effect of pH on adsorption of organic acids and phenolic compounds by amberlite ira 67 resin. *Jurnal Teknologi* 81.
- Hayawin, Z.N., Syirat, Z.B., Ibrahim, M.F., Faizah, J.N., Astimar, A.A., Noorshamsiana, A.W., Ropandi, M., Nursulihatimarsyila, A.W., and Abd-Aziz, S. 2023. Pollutants removal from palm oil mill effluent (POME) final discharge using oil palm kernel shell activated carbon in the up-flow continuous

- adsorption system. *International Journal of Environmental Science and Technology* 20, 4325–4338.
- Ho, Q.N., Lau, W.J., Jaafar, J., Othman, M.H.D., and Yoshida, N. 2025. Membrane technology for valuable resource recovery from palm oil mill effluent (POME): a review. *Membranes* 15, 138.
- Hoe, B.C., Chan, E., Nagasundara Ramanan, R., and Ooi, C.W. 2020. Recent development and challenges in extraction of phytonutrients from palm oil. *Comprehensive Reviews in Food Science and Food Safety* 19, 4031–4061.
- Huang, J., and Zhang, H. 2020. Redox reactions of iron and manganese oxides in complex systems. *Frontiers of Environmental Science & Engineering* 14, 76.
- Hubicki, Z., and Koodynsk, D. 2012. Selective removal of heavy metal ions from waters and waste waters using ion exchange methods, in: Kilislioglu, A. (Ed.), *ion exchange technologies*. Intech Open.
- Jatoi, A.S., Nguyen, H.M., Ahmed, J., and Jeyapaul, A. 2023. Bio-sorbents derived from agricultural biomass for the removal of emerging pollutants and its adsorption mechanisms. *Journal of the Iranian Chemical Society* 20, 2457–2470.
- Jumadi, J., Kamari, A., and Wong, S.T.S. 2020. Water quality assessment and a study of current palm oil mill effluent (POME) treatment by ponding system method. *IOP Conference Series: Materials Science and Engineering* 980, 012076.
- Jumasiah, A., Chuah, T.G., Gimbon, J., Choong, T.S.Y., and Azni, I. 2005. Adsorption of basic dye onto palm kernel shell activated carbon: sorption equilibrium and kinetics studies. *Desalination* 186, 57–64.
- Kacaribu, A.A., Aisyah, Y., and Febriani, Darwin. 2025. Development of wastewater treatment methods for palm oil mill effluent (POME): a comprehensive review. *Resources Chemicals and Materials* 4, 100130.
- Kamari, A., Jumadi, J., Abdul Rahim, N., Fatimah, I., and Sukkaew, A. 2021. A brief review of physico-chemical treatment techniques for palm oil mill effluent (POME). *Current Applied Science and Technology* 22.
- Keyvan Hosseini, M., Liu, L., Keyvan Hosseini, P., Bhattacharyya, A., Lee, K., Miao, J., and Chen, B. 2022. Review of hollow fiber (HF) membrane filtration technology for the treatment of oily wastewater: applications and challenges. *Journal of Marine Science and Engineering* 10, 1313.
- Khadaroo, S.N.B.A., Poh, P.E., Gouwanda, D., and Grassia, P. 2019. Applicability of various pretreatment techniques to enhance the anaerobic digestion of Palm oil Mill effluent (POME): A review. *Journal of Environmental Chemical Engineering* 7, 103310.
- Khairuddin, M.N., Zakaria, A.J., Md Isa, I., Jol, H., Rahman, W.Mohd.N.W.A., and Salleh, Mohd.K.S. 2016. The potential of treated palm oil mill effluent (pome) sludge as an organic fertilizer. *AGRIVITA Journal of Agricultural Science* 38.
- Khan, I.U., Rahman, M.A., Othman, M.H.D., Iftikhar, M., Jilani, A., Mehmood, S., Shakoor, M.B., Rizwan, M., and Yong, J.W.H. 2025. Innovative solutions for palm oil mill effluent treatment: a membrane technology perspective. *ACS Environmental Science and Technology Water* 5, 3538–3562.
- Khongkliang, P., Chalearmkul, K., Boonloh, K., Kanjanasombun, N., Darnsawat, T., Boonnorat, J., Kadier, A., Aryanti, P.T.P., and Phalakornkule, C. 2024. Performance of combined organic precipitation, electrocoagulation, and electrooxidation in treating anaerobically treated palm oil mill effluents. *Applied Water Science* 14, 222.
- Langley, L.A., and Fairbrother, D.H. 2007. Effect of wet chemical treatments on the distribution of surface oxides on carbonaceous materials. *Carbon* 45, 47–54.
- Liew, W.L., Kassim, Mohd.A., Muda, K., Loh, S.K., and Affam, A.C. 2015. Conventional methods and emerging wastewater polishing technologies for palm oil mill effluent treatment: a review. *Journal of Environmental Management* 149, 222–235.
- Lin, D., and Xing, B. 2008. Adsorption of phenolic compounds by carbon nanotubes: role of aromaticity and substitution of hydroxyl groups. *Environmental Science & Technology* 42, 7254–7259.

- Lin, J., and Wang, L. 2009. Comparison between linear and non-linear forms of pseudo-first-order and pseudo-second-order adsorption kinetic models for the removal of methylene blue by activated carbon. *Frontiers of Environmental Science & Engineering* 3, 320–324.
- Liu, P. 2007. Polymer modified clay minerals: a review. *Applied Clay Science* 38, 64–76.
- Low, S.S., Bong, K.X., Mubashir, M., Cheng, C.K., Lam, M.K., Lim, J.W., Ho, Y.C., Lee, K.T., Munawaroh, H.S.H., and Show, P.L. 2021. Microalgae cultivation in palm oil mill effluent (POME) treatment and biofuel production. *Sustainability* 13, 3247.
- Mahmoodi, M., and Pishbin, E. 2025. Ozone-based advanced oxidation processes in water treatment: recent advances, challenges, and perspective. *Environmental Science and Pollution Research* 32, 3531–3570.
- Mapossa, A.B., Mhike, W., Adalima, J.L., and Tichapondwa, S. 2021. Removal of organic dyes from water and wastewater using magnetic ferrite-based titanium oxide and zinc oxide nanocomposites: a review. *Catalysts* 11, 1543.
- Mathews, A.P., and Zayas, I. 1989. Particle size and shape effects on adsorption rate parameters. *Journal of Environmental Engineering* 115, 41–55.
- Mohammad, S., Baidurah, S., Kobayashi, T., Ismail, N., and Leh, C.P. 2021. Palm oil mill effluent treatment processes: a review. *Processes* 9, 739.
- Mohammed, R.R., Ketabchi, M.R., and McKay, G. 2014. Combined magnetic field and adsorption process for treatment of biologically treated palm oil mill effluent (POME). *Chemical Engineering Journal* 243, 31–42.
- Mondal, P., Majumder, C.B., and Mohanty, B. 2008. Effects of adsorbent dose, its particle size and initial arsenic concentration on the removal of arsenic, iron and manganese from simulated ground water by Fe₃₊ impregnated activated carbon. *Journal of Hazardous Materials* 150, 695–702.
- Mozetič, M. 2019. Surface Modification to Improve Properties of Materials. *Materials* 12, 441.
- Nageeb, M. 2013. Adsorption technique for the removal of organic pollutants from water and wastewater, in: Rashed, M.N. (Ed.), *organic pollutants - monitoring, risk and treatment*. Intech Open.
- Naswir, M., Jalius, J., Natalia, D., Arita, S., and Wibowo, Y.G. 2021. Adsorption of mercury using different types of activated bentonite: a study of sorption, kinetics, and isotherm models. *Jurnal Rekayasa Kimia Lingkungan* 15, 123–131.
- Ng, W.J., Goh, A.C.C., and Tay, J.H. 1988. Palm oil mill effluent treatment liquid-solid separation with dissolved air flotation. *Biological Wastes* 25, 257–268.
- Nur, M.M.A., Garcia, G.M., Boelen, P., and Buma, A.G.J. 2021. Influence of photodegradation on the removal of color and phenolic compounds from palm oil mill effluent by *Arthrospira platensis*. *Journal of Applied Phycology* 33, 901–915.
- Obileke, K., Nwokolo, N., Makaka, G., Mukumba, P., and Onyeaka, H. 2021. Anaerobic digestion: technology for biogas production as a source of renewable energy—a review. *Energy & Environment* 32, 191–225.
- Pandey, S.R., Jegatheesan, V., Baskaran, K., and Shu, L. 2012. Fouling in reverse osmosis (RO) membrane in water recovery from secondary effluent: a review. *Reviews in Environmental Science and Bio Technology* 11, 125–145.
- Panwar, N.L., and Pawar, A. 2022. Influence of activation conditions on the physicochemical properties of activated biochar: a review. *Biomass Conversion and Biorefinery* 12, 925–947.
- Parthasarathy, S., Mohammed, R.R., Fong, C.M., Gomes, R.L., and Manickam, S. 2016. A novel hybrid approach of activated carbon and ultrasound cavitation for the intensification of palm oil mill effluent (POME) polishing. *Journal of Cleaner Production* 112, 1218–1226.
- Perelomov, L., Mandzhieva, S., Minkina, T., Atroshchenko, Y., Perelomova, I., Bauer, T., Pinsky, D., and Barakhov, A. 2021. The synthesis of organoclays based on clay minerals with different structural expansion capacities. *Minerals* 11, 707.

- Poh, P.E., Ong, W.Y.J., Lau, E.V., and Chong, M.N. 2014. Investigation on micro-bubble flotation and coagulation for the treatment of anaerobically treated palm oil mill effluent (POME). *Journal of Environmental Chemical Engineering* 2, 1174–1181.
- Pradhan, B.K., and Sandle, N.K. 1999. Effect of different oxidizing agent treatments on the surface properties of activated carbons. *Carbon* 37, 1323–1332.
- Pursell, C.J., Chandler, B.D., Manzoli, M., and Boccuzzi, F. 2012. CO adsorption on supported gold nanoparticle catalysts: application of the temkin model *The Journal of Physical Chemistry C* 116, 1117–1125.
- Rahmanian, N., Jafari, S.M., and Galanakis, C.M. 2014. Recovery and removal of phenolic compounds from olive mill wastewater. *Journal of the American Oil Chemists' Society* 91, 1–18.
- Rehman, A., Park, M., and Park, S.J. 2019. Current progress on the surface chemical modification of carbonaceous materials. *Coatings* 9, 103.
- Reineke, W. 2001. Aerobic and anaerobic biodegradation potentials of microorganisms, in: Beek, B. (Ed.), *biodegradation and persistence. The Handbook of Environmental Chemistry.* Springer-Verlag, Berlin/Heidelberg 1–161.
- Revellame, E.D., Fortela, D.L., Sharp, W., Hernandez, R., and Zappi, M.E. 2020. Adsorption kinetic modeling using pseudo-first order and pseudo-second order rate laws: a review. *Cleaner Engineering and Technology* 1, 100032.
- Saadi, R., Saadi, Z., Fazaeli, R., and Fard, N.E. 2015. Monolayer and multilayer adsorption isotherm models for sorption from aqueous media. *Korean Journal of Chemical Engineering*. 32, 787–799.
- Samiey, B., Cheng, C.H., and Wu, J. 2014. Organic-inorganic hybrid polymers as adsorbents for removal of heavy metal ions from solutions: a review. *Materials* 7, 673–726.
- Scheuermann Filho, H.C., Beck Saldanha, R., Gravina Da Rocha, C., and Cesar Consoli, N. 2021. Sustainable binders stabilizing dispersive clay. *Journal of Materials in Civil Engineering* 33, 06020026.
- Schideman, L.C., Mariñas, B.J., Snoeyink, V.L., Qi, S., and Campos, C. 2007. Three-component adsorption modeling to evaluate and improve integrated sorption–membrane processes. *Environmental Science & Technology* 41, 6547–6553.
- Shavandi, M.A., Haddadian, Z., Ismail, M.H.S., Abdullah, N., and Abidin, Z.Z. 2012. Removal of Fe(III), Mn(II) and Zn(II) from palm oil mill effluent (POME) by natural zeolite. *Journal of the Taiwan Institute of Chemical Engineers* 43, 750–759.
- Singh, M., and Srivastava, R.K. 2011. Sequencing batch reactor technology for biological wastewater treatment: a review. *Asia-Pacific Journal of Chemical Engineering* 6, 3–13.
- Solomakou, N., and Goula, A.M. 2021. Treatment of olive mill wastewater by adsorption of phenolic compounds. *Reviews in Environmental Science and Bio Technology* 20, 839–863.
- Song, X., Zhang, Y., Yan, C., Jiang, W., and Chang, C. 2013. The Langmuir monolayer adsorption model of organic matter into effective pores in activated carbon. *Journal of Colloid and Interface Science* 389, 213–219.
- Stefan, M.I. 2017. UV/Hydrogen peroxide process. *Water Intell Online* 16, 7–122.
- Subhash Bhatia, A.L.A., Norliza Ibrahim., and Suzylawati Ismail. 1970. Coagulation-sedimentation-extraction pretreatment methods for the removal of suspended solids and residual oil from palm oil mill effluent (Pome). *IIUM Engineering Journal* 3.
- Swartzen-Allen, S.L., and Matijevic, E. 1974. Surface and colloid chemistry of clays. *Chemical Reviews* 74, 385–400.
- Taher, T., Munandar, A., Mawaddah, N., Syamsuddin Wisnubroto, M., Siregar, P.M.S.B.N., Palapa, N.R., Lesbani, A., and Wibowo, Y.G. 2023. Synthesis and characterization of montmorillonite – Mixed metal oxide composite and its adsorption performance for anionic and cationic dyes removal. *Inorganic Chemistry Communications* 147, 110231.
- Taher, T., Putra, R., Sari, N.K., Zurfi, A., Rohman, A., Kurnia, I., Maulana, S., Kartika, K., Wibowo, Y.G., Rianjanu, A., and Lesbani, A. 2023. Insight into the pyrolysis behavior of the drained Sumatra peat

- soil and the characteristics of the resulting biochar for carbon dioxide (CO₂) capture. *Bioresource Technology Reports* 24, 101680.
- Taher, T., Yu, Z., Melati, E.K.A., Munandar, A., Aflaha, R., Triyana, K., Wibowo, Y.G., Khairurrijal, K., Lesbani, A., and Rianjanu, A. 2024. Enabling dual-functionality material for effective anionic and cationic dye removal by using Nb₂O₅/MgAl-LDH nanocomposites. *Journal of Hazardous Materials Letters* 5, 100103.
- Tang, L., Xie, X., Li, C., Xu, Y., Zhu, W., and Wang, L. 2022. Regulation of structure and anion-exchange performance of layered double hydroxide: function of the metal cation composition of a brucite-like layer. *Materials* 15, 7983.
- Wibowo, Y.G., Anwar, D., Safitri, H., Setiawan, A., Sudibyoy, S., Yuliansyah, A.T., and Murti Petrus, H.T.B. 2025. Comprehensive review of hybrid absorption-adsorption techniques for chromium removal from wastewater using magnetite-zeolite suspended in glycol slurry. *Colloids and Surfaces: Environmental Aspects* 100066.
- Wibowo, Y.G., Anwar, D., Safitri, H., Setiawan, A., Supriyatna, Y.I., Sudibyoy, Yuliansyah, A.T., and Petrus, H.T.B.M. 2025. A comprehensive review of layered double hydroxide/magnetite-biochar for chromium removal from wastewater. *Bioresource Technology Reports* 29, 102034.
- Wibowo, Y.G., Anwar, D., Safitri, H., Surya, I., Sudibyoy, S., Yuliansyah, A.T., and Murti Petrus, H.T.B. 2025. Functionalized magnetite-biochar with live and dead bacteria for adsorption-biosorption of highly toxic metals: Cd, Hg, and Pb. *Next Materials* 6, 100487.
- Wibowo, Y.G., Ramadan, B.S., Sudibyoy, S., Safitri, H., Rohman, A., and Syarifuddin, H. 2023. Efficient remediation of acid mine drainage through sustainable and economical biochar-CaO composite derived from solid waste. *Environment, Development and Sustainability* 26, 16803–16826.
- Wibowo, Y.G., Safitri, H., Cahyani, K., Sudibyoy, Rohman, A., Yuliansyah, A.T., Petrus, H.T.B.M., Ramadan, B.S., Anis, T.M., and Syarifuddin, H. 2025. Enhanced modified magnetite bentonite-cao/fecl₃ from solid waste for highly efficient methylene blue removal. *Global NEST Journal* 27, 1–14.
- Wibowo, Y.G., Safitri, H., Kusumawati, Aini, W.D., Farantino, R., Ginting, S.B., Rinovian, A., Kurniawan, S.B., Khairurrijal, K., Taher, T., Kusumaningrum, W.B., Sudibyoy, S., Yuliansyah, A.T., and Petrus, H.T.B.M. 2025. Biochar MMT ZnAl LDH composite materials derived from solid waste for heavy metal removal in artificial acid mine drainage. *Scientific Reports* 15, 14914.
- Wibowo, Y.G., Sudibyoy, Naswir, M., and Ramadan, B.S. 2022. Performance of a novel biochar-clamshell composite for real acid mine drainage treatment. *Bioresource Technology Reports* 17, 100993.
- Xu, C., Sun, W.Z., Qin, X.L., Jia, Y.-X., Yu, S.-T., and Xian, M. 2019. Effective adsorption of phenolic compounds by functional group modified resins: behavior and mechanism. *Separation Science and Technology* 54, 467–477.
- Yang, Z., Liu, J., Zhang, A., Liu, Y., Lei, J., Liu, P., and Liu, Z. 2025. Sustainable application of functionalized resins in adsorbing and recycling aromatic compounds from complex wastewater systems: Exploration of synthesis strategies, performance predictions, and interaction mechanisms. *Separation and Purification Technology* 361, 131369.
- Yashni, G., Al-Gheethi, A., Radin Mohamed, R.M.S., Arifin, S.N.H., and Mohd Salleh, S.N.A. 2021. Conventional and advanced treatment technologies for palm oil mill effluents: a systematic literature review. *Journal of Dispersion Science and Technology* 42, 1766–1784.
- Zainal, N.H. 2018. A review on the development of palm oil mill effluent (pome) final discharge polishing treatments. *Journal of Petroleum Research* 29, 528–540.
- Zehtab, B., and Tarighat, A. 2018. Molecular dynamics simulation to assess the effect of temperature on diffusion coefficients of different ions and water molecules in C-S-H. *Mech Time-Depend Mater* 22, 483–497.
- Zeng, X., Zhang, G., Zhu, J., and Wu, Z. 2022. Adsorption of heavy metal ions in water by surface functionalized magnetic composites: a review. *Environmental Science: Water Research & Technology* 8, 907–925.

- Zhu, S., Ho, S.-H., Jin, C., Duan, X., and Wang, S. 2020. Nanostructured manganese oxides: natural/artificial formation and their induced catalysis for wastewater remediation. *Environmental Science.: Nano* 7, 368–396.
- Zinatizadeh, A.A., Ibrahim, S., Aghamohammadi, N., Mohamed, A.R., Zangeneh, H., and Mohammadi, P. 2017. Polyacrylamide-induced coagulation process removing suspended solids from palm oil mill effluent. *Separation Science and Technology* 52, 520–527.